

424/10 ถนนกาญจนาภิเษก แขวงดอกไม้ เขตประเวศ กรุงเทพมหานคร 10250 โทร. 662-0400401 โทรสาร 662-0400402 424/10 Kanchanapisek Road, Dokmai, Prawet, Bangkok 10250 Thailand Tel. 662-0400401 Fax. 662-0400402

SPECIFICATION CBS (GRANULE)

Accelerator

Chemical Name

N-Cyclohexyl-2-

benzothiazole sulfonamide

	denzounazoie suitonamide		
Molecular Formula	6	$C_{13}H_{16}N_2S_2$	
Molecular Structure	33/106	N C-S-N-CH	CH ₂ -CH ₃ >CH ₃
Molecular Weight	10	264.4	
Gravity	107	1.31-1.34	
CAS NO.	Mario	95-33-0	
Specification			
200	YC'	10	
Appearance	Powder	Oil-coated Powder	Granule
Da M	Powder	Oil-coated Powder Grayish White	Granule
	Powder 98.0	XC.	Granule 98.0
Da M		Grayish White	
Initial M.P. °C ≥	98.0	Grayish White 98.0	98.0
Initial M.P. °C ≥ Loss on Drying % ≤	98.0	Grayish White 98.0 0.30	98.0 0.30
Initial M.P. °C ≥ Loss on Drying % ≤ Ash % ≤	98.0 0.30 0.30	Grayish White 98.0 0.30 0.30	98.0 0.30 0.30
Initial M.P. °C ≥ Loss on Drying % ≤ Ash % ≤ Free Amine % ≤	98.0 0.30 0.30 0.50	Grayish White 98.0 0.30 0.30 0.50	98.0 0.30 0.30 0.50

Packing

25 kg/bag

Storage Life 24 Months

Properties

Solublein benzene, dichloromethane, carbon tetrachloride, ethyl acetate, acetone, slightly soluble in ethanol and petrol. Insoluble in water.

This is a delayed accelerator, with good anti-scorching quality, as well as short vulcanizing duration, which would improve the tensile stress of vulcanization. Minor discoloration, no blooming, antioxidant quality of vulcanization is superior. When applied, adding zinc oxide and stearic acid are necessary to strengthen the effect of TMTD, TMTM, ZDMC, DPG or other alkaline accelerators that are used as second accelerator, as well as being activated by MBT and MBTS.







QC/PB06-02-S0

Re. 00 / Date: 1.11.2020